

SPECIFICATION:

BUTYL RECLAIM:

Chemical Properties:

Ash %	2 - 8
Carbon Black %	28 Min.
Acetone Extract %	6 - 12
Volatile Matter %	1 Max.
RHC By Difference %	50 Min.

Physical Properties:

Specific Gravity gm/cc	1.08 - 1.14
Tensile Strength kg/cm ²	75 Min.
Elongation at Break %	470 Min.
Mooney Viscosity ML (1+4) @ 100 ⁰ C.	35 - 55
Hardness Shore A	52 - 62